

Technical Data Sheet / Specifications

PRODUCT NAME : Natural White
FSC™ certified (FSC™ C168382)

| Quality/Attributed | | Unit | Testing Method | 70 | 80 | 100 |
|--------------------|-----|------------------|---------------------|---------|---------|---------|
| Basis Weight | | g/m ² | Electronic Balance | 69±3% | 79±3% | 98±3% |
| Thickness | | micron | Micro Meter | 85±3 | 94±3 | 116±3 |
| Moisture Content | | % | Dry Oven 105°C,3hrs | 6.0±0.5 | 6.0±0.5 | 6.2±0.5 |
| Brightness | | % | Elrepho | 85 ↑ | 85 ↑ | 85 ↑ |
| Whiteness | | % | | 100 ↑ | 100 ↑ | 100 ↑ |
| Opacity | | % | | - | - | - |
| Smoothness | F.S | sec | Bekk Type | 30 ↑ | 30 ↑ | 30 ↑ |
| | T.S | | | 30 ↑ | 30 ↑ | 30 ↑ |
| Tensile | MD | kgf | Tensile Tester TMI | 5.0 ↑ | 5.0 ↑ | 5.0 ↑ |
| Wax | | A | Pine Wax | 10 ↑ | 10 ↑ | 10 ↑ |
| Size | | sec | Stockigt | 10 ↑ | 10 ↑ | 10 ↑ |

CERTIFY THE ABOVE STATEMENT QUALITY TO BE TRUE AND CORRECT