

Technical Data Sheet / Specifications

PRODUCT NAME : Uncoated Woodfree / Green Card 100%ECO

Quality/Attributed		Unit	Std.	200	250
Basis Weight		g/m ²	ISO 536	200±5	250±5
Single Sheet Thickness		µm	ISO 534	235±15	285±15
Roughness Bendtsen	Top	ml./min.	ISO 8791-2	150max	150max
Roughness Bendtsen	Bottom	ml./min.	ISO 8791-2	150max	150max
ISO Brigutness (C/2)		-	ISO 2470-1	75min	75min
Opacity		%	ISO 2471	90min	90min
Shade Difference (Delta E C/2)		-	ISO 2470-1	1max	1max
Shade Strength (Wax Pick)	Top	A	TAPPI T459	14min	14min
Shade Strength (Wax Pick)	Bottom	A	TAPPI T459	14min	14min

Target Shade : a*(C/2) : -1.3 b*(C/2):2.70 L*(C/2):92.3

Test Condition %RH 50±2 Temp. 23±1 degree