

Technical Data Sheet / Specifications

PRODUCT NAME : Uncoated Woodfree / Green Offset 100%ECO

Quality/Attributes		Unit	Testing Standard	80	100	120
Grammage		(g/m ²)	ISO 536	80±2	100±2	120±3
Single Sheet Thickness		µm	ISO 534	99±5	125±10	150±10
Roughness Bendtsen	Top	ml/min	ISO 8791-2	180max		
Roughness Bendtsen	Bottom	ml/min	ISO 8791-2	180max		
ISO Brightness (C/2)		-	ISO 2470-1	70min		
Opacity		%	ISO 2471	86min	88min	90min
Shade Difference (Delta E C/2)		-	ISO 2470-1	1max		
Surface Strength (Wax Pick)	Top	A	TAPPI T459	14min		
Surface Strength (Wax Pick)	Bottom	A	TAPPI T459	14min		

Target Shade : a*(C/2) : -1.3 b*(C/2):3.20 L*(C/2):92.3

Test Condition %RH 50±2 Temp. 23±1 degree