

### Technical Data Sheet / Specifications

PRODUCT NAME : Uncoated Woodfree / Green Card 100%ECO

Quality/Attributed		Unit	Testing Method	150
Basis Weight		g/m <sup>2</sup>	ISO 536	150±5
Single Sheet Thickness		µm	ISO 534	242±20
Roughness Bendtsen	Top	ml./min.	ISO 8791-2	600min
Roughness Bendtsen	Bottom	ml./min.	ISO 8791-2	600min
CIE Whiteness(D65)		-	ISO 11475	143±3
ISO Brigutness (C/2)		-	ISO 2470-1	92±3
Shade Difference (Delta E C/2)		-	ISO 2470-1	1max
Water Absorptiveness(Cobb60sec)	Top	g/m <sup>2</sup>	ISO 535	35max
Water Absorptiveness(Cobb60sec)	Bottom	g/m <sup>2</sup>	ISO 535	35max
Surface Strength (Wax Pick)	Top	A	TAPPI T459	14min
Surface Strength (Wax Pick)	Bottom	A	TAPPI T459	14min
Dirt (TAPPI)		ppm	TAPPI T563	5max

Target Shade : a\*(C/2) :2.9    b\*(C/2):-6.9    L\*(C/2):94

Test Condition %RH 50±2 Temp. 23±1 degree

