

Technical Data Sheet / Specifications

PRODUCT NAME : Green Plus 50%ECO

Quality/Attributed		Unit	Testing Method	60	70	80	100
Grammage		gsm.	ISO 536	60±3	70±3	80±3	100±3
Single Sheet Thickness		micron	ISO 534	78±5	87±5	97±5	116±5
Roughness Bendtsen	Top	ml./min.	ISO 8791-2	180max			
	Bottom	ml./min.	ISO 8791-2	180max			
CLE Whiteness (D65)		-	ISO 11475	153±2			
ISO Brightness (C/2)		-	ISO 2470-1	90±2			
Opacity		-	ISO 2471	85min	88min	90min	94min
Shade Difference (Delta E C/2)		-	ISO 2470-1	1max			
Surface Strength (Wax Pick)	Top	A	TAPPI T459	14min			
	Bottom	A	TAPPI T459	14min			
Moisture Content (DCS)		%	DCS	6.5max			

Target Shade: a*(C/2): 3.44 b*(C/2):-10.50 L*(C/2):90.00

Test Condition %RH 50±2, Temp. 23±1 degree