



Technical Data Sheet / Specifications

PRODUCT NAME : ลาร์ตการ์ด 1/S Armore (FSC Mix Credit)

Items		Unit	Test Method	Tolerance	Standard				
Grammage		g/m ²	GB/T451.2 ISO536	±3%	230g	250g	300g	350g	400g
Thickness		µm	GB/T451.3 ISO534	±3%	310	345	415	485	555
Stiffness	MD	mN · m	GB/T22364	±15%	8.5	9.5	15	23	28.5
	CD	mN · m	ISO2493	±15%	4	5	7	11	15
Moisture		%	GB/T462 ISO2493	±1.5	7.5				
Surface Roughness		µm	GB/T22363 ISO8791-4	≤	1.5				
Brightness	TOP	%	GB/T7974	±3	90				
	BACK		ISO2470-2		88				
75° Gloss-Top		%	GB/T8941 ISO8254	≥	45				
IGT Picking-Top		m/s	GB/T22365 ISO3783	≥	1.3				
Ply Bond		J/m ²	GB/T26203 TAPPI569	≥	130				
Cobb-Top (60s)		g/m ²	GB/T1540 ISO535	≤	60				

Testing Condition : Temperature : (23±1) °C Relative Humidity : (50±2)%

