

Technical Data Sheet / Specifications

PRODUCT NAME : White Card Paper

| Quality/Attributed | Unit | Std. | 120gsm. | 150gsm. | 180gsm. | 210gsm. | 240gsm. |
|---------------------------------------|------------------|------------|---------|---------|---------|---------|---------|
| Basis Weight | g/m ² | ISO 536 | 120±6 | 150±8 | 180±9 | 210±10 | 240±12 |
| Thickness | micron | ISO 534 | 155±15 | 190±15 | 230±15 | 245±15 | 275±15 |
| Roughness Bendtsen Top Side | ml/min | ISO 8791-2 | 250max | 250max | 250max | 250max | 250max |
| Roughness Bendtsen Bottom Side | ml/min | ISO 8791-2 | 250max | 250max | 250max | 250max | 250max |
| CIE Whiteness | - | ISO 11475 | 138±3 | 138±3 | 138±3 | 138±3 | 138±3 |
| ISO Brihtness | - | ISO 2470-1 | 94±2 | 94±2 | 94±2 | 94±2 | 94±2 |
| Surface Streng (Wax Pick) Top Side | A | TAPPI T459 | 14min | 14min | 14min | 14min | 14min |
| Surface Streng (Wax Pick) Bottom Side | A | TAPPI T459 | 14min | 14min | 14min | 14min | 14min |

Test Condition %RH 50±2 Temp. 23±1 degree

