

Technical Data Sheet / Specifications

Product Name : CKB Nude - StoraEnso

Quality/Attributed		Unit	Tolerance	Testing Method	205	230	255
Grammage		g/m ²	±4%	ISO 536	205	230	255
Thickness		micron	±5%	ISO 534	380	445	495
Bending moment Taber 15°	MD	mNm	-15%	TAPPI 489	12.9	19.2	26.3
	CD	mNm	-15%	TAPPI 489	5.1	7.7	10.5
Bending resistance L&W 15°	MD	mN	-15%	ISO 2493	266	400	544
	CD	mN	-15%	ISO 2493	106	160	218
Moisture		%	±1	ISO 287	7.5	7.5	7.5
Surface Smoothness Bendtsen	Top	ml/min	max 700	SCAN P 84:02	400	400	400
	Reverse	ml/min	max 2000	SCAN P 84:02	700	700	700
Tearing resistance	MD	mN	-800	TAPPI 496	2900	3400	3900
	CD	mN	-800	TAPPI 496	330	3800	4300
Cobb 60	Top	g/m ²		ISO 535	30	30	30
	Reverse	g/m ²			30	30	30