

Technical Data Sheet / Specifications

Product Name : Atelier - Sappi

Quality/Attributed		Unit	Testing Method	280	300	350
Grammage		g/m ²		280	300	350
Thickness		micron	ISO 534	445	495	595
Bending resistance L&W 15°	MD	mN	ISO 2493	379	465	720
	CD	mN	ISO 2493	190	250	375
Bending moment Taber 15°	MD	mNm	TABERT489-OM-92	18	22.2	35
	CD	mNm	TABERT489-OM-92	9.5	12	18
Bending stiffness Taber 5°	MD	mNm	ISO 2493	31.1	41.7	67.9
	CD	mNm	ISO 2493	16.5	22.5	36.5
Surface Roughness PPS 10 TS		micron	ISO 8791-4	1.3	1.3	1.4
Gloss 75°	Top	%	ISO 8254-1	50	50	50
	Reverse	%	ISO 8254-1	5	5	5