

**Technical Data Sheet / Specifications**

Product Name : KT Kraft Liner  
 FSC™ certified (FSC™ C168382)

|                         |                    |                  |                | TS   |      |      |      |     |
|-------------------------|--------------------|------------------|----------------|------|------|------|------|-----|
| Quality/Attributed      |                    | Unit             | Testing Method | 125  | 140  | 165  | 185  | 235 |
| Basis Weight            |                    | g/m <sup>2</sup> | ISO 536        | 125  | 140  | 165  | 185  | 235 |
| Moisture                |                    | %                | ISO 287        | 6-10 |      |      |      |     |
| Ring Crush (Min)        | N/152.4mm          | ISO 12192        | 140            | 190  | 230  | 290  | 380  |     |
|                         | kg/cm              |                  | 0.94           | 1.27 | 1.54 | 1.94 | 2.54 |     |
|                         | kg/6inch           |                  | 14.3           | 19.4 | 23.5 | 29.6 | 38.7 |     |
| Bursting strength (Min) | kPa                | ISO 2759         | 275            | 350  | 410  | 500  | 640  |     |
|                         | kg/cm <sup>2</sup> |                  | 2.8            | 3.57 | 4.18 | 5.1  | 6.53 |     |
|                         | psi                |                  | 40             | 51   | 59   | 73   | 93   |     |
| Cobb's (2mins)          | Top                | ISO 535          | 30-100         |      |      |      |      |     |
|                         | Bottom             |                  | 40-150         |      |      |      |      |     |

Test Condition %RH 65, Temp. 27°C

