

Technical Data Sheet / Specifications

Product Name : KA Kraft Liner
 FSC™ certified (FSC™ C168382)

Quality/Attributed		Unit	Testing Method	125	150	185	230
Basis Weight		g/m ²	ISO 536	125	150	185	230
Moisture		%	ISO 287	6-10			
Ring Crush (Min)		N/152.4mm	ISO 12192	160	210	280	380
		kg/cm		1.07	1.4	1.87	2.54
		kg/6inch		16.3	21.4	28.6	38.7
Bursting strength (Min)		kPa	ISO 2759	390	460	520	640
		kg/cm ²		3.98	4.69	5.3	6.53
		psi		57	67	75	93
Cobb's (2mins)	Top	g/m ²	ISO 535	30-100			
	Bottom	g/m ²		40-120			
Cobb's (30mins)	Top	g/m ²	ISO 535	155max			

Test Condition %RH 65±2 Temp. 27±1°C

